

TECHNICAL DATA SHEET

RIGID PVC : Medium Impact extrusion grade for various profiles

Eigenschappen <i>Propriétés</i> Properties <i>Eigenschaften</i>	Normen <i>Normes</i> Standards <i>Normen</i>	Eenheden <i>Unités</i> Units <i>Einheiten</i>	Waarden <i>Valeurs</i> Values <i>Werte</i>
Dichtheid-Densité-Density-Dichte	ISO R1183	-	1.52
UV-Stability	ISO 10 5 A02	-	3 - 2
Vicat Verwekingspunt 5 KG Points Vicat 5 KG Vicat Point 5 KG Vicat Erweichungspunkt 5 KG	ISO 306	°C	77
Vloeigrens – Contrainte au seuil Stress at Yield - Streckspannung	ISO 527	M Pa	40,50
Breuksterkte – Contrainte à la rupture – Stress at break - Zugfestigkeit	ISO 527	M Pa	40
Breukverlenging – Allongement à la rupture – Elongation at break - Reisdehnung	ISO 527	%	160
Buigmodulus – Module de flexion Flexural Modulus - Biegemodulus	ISO 178	M Pa	3700
Kerfslagvastheid (Charpy) – Choc Charpy entaillé – Notched Charpy impact – Kerbschlagzähigkeit (Charpy)	ISO 179	kJ/m ²	> 7
Brandgedrag Classement au feu Fire rating Brandverhalten	Din 4102 NFP92-501/512 BS476 part 7 NEN 6065 NEN 6066	-	B1 M1 class 1-2 class 2 7.3 m-1