

ROXANE

SHOW COLLECTION

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufting 1/10" cut pile Tufté 1/10" cut pile Getuftet 1/10" cut pile Getuft 1/10" cut pile	FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	EN ISO 105-B02 ≥ 5-6
PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL	100% PA	COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥ 4-5
SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG	Ultratex® back	FIRE RESISTANCE COMPOTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 C _{FL} -s1 if glued
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	± 450 gr/m²	WIDTH LARGEUR BREITE BREEDTE	EN ISO 3018 ca. 400 cm
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	± 1.290 gr/m²	UPEC CERTIFICATION	U2sP2E1C0 n° 07/231
PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE	± 4 mm		
TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTAAL DIKTE	± 8 mm		
TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN	± 236.400/m²		
PRODIS / GUT	4DEC5FAE		
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 22 - LC1		



ITC CO BV
Kanegemstraat 15, B-8700 Tielt
itc-carpet.com

